

	<b>Catalyst level – volume of catalyst (ml)</b>				
<b>Volume resin/gelcoat</b>	<b>1% (22-25°C)</b>	<b>1.5% (20-22°C)</b>	<b>2% (18-20°C)</b>	<b>3% (18°C)</b>	
<b>1 kg</b>	<b>10</b>	<b>15</b>	<b>20</b>	<b>30</b>	
<b>2 kg</b>	<b>20</b>	<b>30</b>	<b>40</b>	<b>60</b>	
<b>3 kg</b>	<b>30</b>	<b>45</b>	<b>60</b>	<b>90</b>	
<b>4 kg</b>	<b>40</b>	<b>60</b>	<b>80</b>	<b>120</b>	
<b>5 kg</b>	<b>50</b>	<b>75</b>	<b>100</b>	<b>150</b>	