

# Application Instructions

## Woodoc 55 Exterior Sealer

### WHERE TO USE PRODUCT

For exterior wood. Where a tinted, gloss sealer with high film build & extra UV-protection is required. Provides excellent UV-protection and water repellence. **Do not use on hard, dense timber decks.**

### HOW TO PREPARE THE SURFACE

**General:** Wood must always be clean, dry & smooth before use of product. Never wash/wipe wood with water before use of product.

**New wood:** Sand until smooth. Remove dust with clean, dry cloth. Then wipe with mineral turpentine.

**Previously varnished wood:** Remove varnish by sanding/using paint stripper. Neutralise paint stripper according to manufacturer's instructions. Allow wood to dry completely. Sand until smooth. Remove dust with clean, dry cloth. Then wipe with mineral turpentine.

**Oiled wood:** Sand until smooth. Then scrub well with Woodoc SteelWool and mineral turpentine. Clean off residue with clean, dry cloth. Allow surface to dry.

**Wood previously treated with Woodoc:** Scrub well with Woodoc SteelWool and mineral turpentine. Clean off residue with clean, dry cloth. Allow surface to dry.

### HOW TO APPLY THE PRODUCT

**Stir well before and during application to ensure colour consistency.** Do not shake or dilute product. Apply product with good quality brush. Apply first coat until surface remains evenly glossy for at least 10 minutes after application. Apply more product to dull/dry areas. Allow coat to dry **completely**. Sand lightly with Woodoc SteelWool. Remove dust with clean, dry cloth. Then wipe with mineral turpentine. Apply two more coats in the same way. Do not sand after third coat. **Always apply a minimum of three coats.** Proper film build on surface is essential. Seal end grain very well.

### COVERAGE

± 3,3 m<sup>2</sup> per litre (for three coats)

### WARRANTY

Rekara Mills (Pty) Ltd warrants that this product, as consigned from our factory, was subject to strict quality assurance tests and meets durability, safety, and quality standards. The product must be used, stored and handled strictly according to the instructions and warnings provided on the container and/or any pamphlet attached thereto or made available with the product. All such instructions and warnings must be strictly adhered to otherwise Rekara Mills (Pty) Ltd accepts no responsibility for the use or performance of this product.

# Gebruiksaanwysings

## Woodoc 55 Buitenshuise Verseëlaar

### WAAR OM PRODUK TE GEBRUIK

Vir buitenshuise gebruik. Waar 'n getinte, glansafwerking met sterk oppervlaklaag en ekstra UV-beskerming verlang word. Bied uitstekende UV-beskerming en is ook waterwerend. **Moenie op harde, digte houtdekke gebruik nie.**

### HOE OM DIE OPPERVLAK VOOR TE BEREI

**Algemeen:** Hout moet altyd skoon, droog en glad wees voor gebruik van produk. Moet nooit hout met water was/afvee voor gebruik van produk nie.

**Nuwe hout:** Skuur glad. Vee stof af met skoon, droë lap. Vee dan af met minerale terpentyn.

**Voorheen verniste hout:** Skuur vernis af/gebruik verfstroper. Neutraliseer verfstroper volgens vervaardiger se instruksies. Laat hout heeltemal droog word. Skuur glad. Vee stof af met skoon, droë lap. Vee dan af met minerale terpentyn.

**Geoliede hout:** Skuur glad. Skrop daarna goed met Woodoc StaalWol en minerale terpentyn. Vee hout af met skoon, droë lap. Laat oppervlak droog word.

**Hout voorheen met Woodoc behandel:** Skrop goed met Woodoc StaalWol en minerale terpentyn. Vee hout af met skoon, droë lap. Laat oppervlak droog word.

### HOE OM DIE PRODUK AAN TE WEND

**Roer goed voor en gedurende aanwending om egalige kleuropbou te verseker.** Moenie produk skud of verdun nie. Wend produk met hoëgehalte kwas aan. Wend eerste laag aan totdat die oppervlak egalig blinknat bly vir ten minste 10 minute na aanwending. Wend nog produk op dowwe/droë kolle aan. Laat produk **heeltemal droog** word. Skuur liggies met Woodoc StaalWol. Vee stof af met skoon, droë lap. Vee dan af met minerale terpentyn. Wend nog 2 lae so aan. Moenie na derde laag skuur nie. **Wend altyd 'n minimum van drie lae aan.** Behoorlike produkopbou op oppervlak is noodsaaklik. Verseël eindgrein baie goed.

### DEKKING

± 3,3m<sup>2</sup> per liter (vir 3 lae)

### WAARBORG

Rekara Mills (Edms.) Bpk. waarborg dat hierdie produk, soos versend vanaf ons fabriek, aan streng gehaltebeheertoetse onderwerp is en aan duursaamheid-, veiligheid- en gehalttestandaarde voldoen. Die produk moet streng volgens die aanwysings en waarskuwings op die houer en/of enige pamflet aan die houer geheg of daarmee saam beskikbaar gemaak, hanteer, geberg en gebruik word. Indien alle sodanige instruksies en waarskuwings nie streng gevolg word nie, aanvaar Rekara Mills (Edms.) Bpk. geen verantwoordelikheid vir die gebruik of werkverrigting van die produk nie.